R-F 9300

Titanium Dioxide

Description

R-F 9300 is Alumina, Zirconia and organic treated rutile pigment which produced by sulphate process. It is designed to give optimum properties over the widest range of applications and characterized by outstanding combination of excellent color, opacity and dispersibility coupled with high exterior durability.

Technical specification

Version: 1.0/2025

Item	Property	
TiO_2 Content, %	Min	94
Relative tinting strength,%	Min	112
Oil absorption, g/100g	Max	20
Moisture 105℃, %	Max	0.5
Sieve residue (325 mesh), %	Max	0.03
Water soluble substance, %	Max	0.5
Specific gravity, g/cm3	4.0	
PH	6.0-9.0	
Standard classification	ISO 591-1: R2	
	ASTM D476-00: Ⅱ, V	
Color index	Pigment white 6	
Packing	25kg/bag, 500kg/bag, 1000kg/bag	
Application	Solvent based, can coating, marine coating, ink,etc.	
Storage	Store in cool, well-ventilated area. Keep away from ignition source, heat and flame. Store in a tightly closed container.	
Handling	Avoid dust formation during handling. Provide appropriate exhaust ventilation at machinery and at places where dust can be generated. In case of insufficient ventilation, wear suitable respiratory equipment. Please see the Material Safety Data Sheets (MSDS) of this product for more safety information prior to use.	

The information set forth herein is to the best of our knowledge reliable and accurate but is not to be construed as a warranty. It is subject to change without notice. For additional information regarding our products or for information concerning current specifications, please contact our Technical Customer Service.

泛华化学 INTER-CHINA CHEMICAL

INTER- CHINA CHEMICAL CO., LTD.
C19 BUILDING,NO.99
JINGSHIWU ROAD,212009
ZHENJIANG,JIANGSU,CHINA.

+86-(0)511-84492112
+86-(0)511-84407555
sales@chinatio2.com
www.chinatio2.com

R-F 9300
Titanium Dioxide

R-F9300 typical application performance

	Thermoplastic acrylic paint[1] (white)	Thermoplastic acrylic paint[2] (gray)
L*	97.20	61.70
b*	0.9	-2.90
20° Gloss	68	/
Contrast radio, %	93.4	/
*Relative tinting strength,% (Reference samples are STD.)	/	102

[1] Thermoplastic acrylic resin solution (27% solid content) TiO_2.
Pigment (TiO_2) volume concentration (PVC)=16%.

[2] Thermoplastic acrylic resin solution(33% solid content), TiO_2, black colorants (Carbon black).
Pigment (TiO_2) volume concentration (PVC)=15%.

The information set forth herein is to the best of our knowledge reliable and accurate but is not to be construed as a warranty. It is subject to change without notice. For additional information regarding our products or for information concerning current specifications, please contact our Technical Customer Service.

泛华化学 INTER-CHINA CHEMICAL
INTER- CHINA CHEMICAL CO., LTD.
C19 BUILDING,NO.99
JINGSHIWU ROAD,212009
ZHENJIANG,JIANGSU,CHINA.
+86-(0)511-84492112
+86-(0)511-84407555
sales@chinatio2.com
www.chinatio2.com